



1160 Nicole Court  
 Glendora, CA 91740  
 800-735-5566 • 909-592-6272  
 Fax: 909-592-7971  
 www.carsonind.com

Specification Grade

# 36-Series Vaults

## FLUSH COVER

### Model:

- 3636-3B Plastic
- 3636-3R Polymer Concrete
- 3660-P1 Polymer Concrete (2 piece)
- 3660-8G Steel T-Cover (2 piece)

## BODY

### Model:

- 3636-18
- 3660-18

## DEPTHS AVAILABLE:



18", 24", 30", 36", 42", 48"

## COLOR AVAILABLE:



Gray

**Note:** For use in non-vehicular traffic situations only. We do not recommend installation in concrete or asphalt. Weights and dimensions may vary slightly.

All information contained in this brochure was current at the time of printing. Because of Carson Industries' policy of ongoing research and development, the Company reserves the right to discontinue or update product information without notice.



TOP VIEW



## Specification Grade

# 3636

## 18" Poly Vaults

### Carson Industries, LLC

1160 Nicole Court  
Glendora, CA 91740  
800-735-5566 • 909-592-6272  
Fax: 909-592-7971  
www.carsonind.com

### RAW MATERIAL SPECIFICATIONS

#### HDPE Structural Foam

Material Property	ASTM Test Method	Typical Value <sup>1</sup>
Type, Class, Category	D 1248	III, A, 3
Density, g/ cm <sup>3</sup>	D 1505	0.950 min., not to exceed 0.965
Tensile Strength, at break, psi	D 638	3,000 to 4,400
Elongation, at break, %	D 638	400
Tensile Impact, ft-lb/in <sup>2</sup>	D 1822	27
Flexural Modulus, psi	D 790	120,000 min., not to exceed 240,000
Low Temperature Brittleness, F50, at °C	D 746	<-76
Hardness, Shore D	D 2240	66
Deflection Temperature, at 66 psi	D 648	150° min., not to exceed 200°
Electrical Dielectric Strength, V/mil	D 149	400 min., not to exceed 600

#### Molded Product<sup>2</sup>

Chemical Resistance	D 543	Very Resistant
Water Absorption	D 570	Less than 1% weight change

<sup>1</sup>The values listed for physical property measurements are nominal values only. Certain physical property measurements are subject to variations consistent with the test methods and are within a generally accepted range for such values.

<sup>2</sup>Test reports available on request.

12/18/02

### SHIPPING INFORMATION

All information contained in this brochure was current at the time of printing. Because of Carson Industries' policy of ongoing research and development, the Company reserves the right to discontinue or update product information without notice.

#### Weight

3636 Cover	25 lbs.
3636-18 Body	49.75 lbs.
3660 Polymer Concrete Cover	448 lbs.
3660-18 Body	80 lbs.

#### Shipping Configuration

3636-18: Unit, 4 assemblies = 64.6 cu. ft.; 293.0 lbs.  
3660-18 Unit, 2 assemblies = 72.0 cu. ft.; 789.5 lbs.